



100% MADE IN THE USA

GelSpools™

APPLICATIONS

Extra Long spools of GelCopper™ premium insulation. Ideal for new installations or to simply replace old or damaged insulation without having to change the copper coils. Good for Indoor or Outdoor. Available in different sizes and with 1/2" or 3/4" insulation thickness.

TECHNICAL SPECS

INSULATION

Low Density Polyethylene Closed Cell Foam

ASTM C 1427-07 compliant

Type I (tubular)

Grade I (insulation material for use on typical commercial system non-crosslinked)

CFC and HCFC gas free.

Water vapor permeability: ASTM E96-00 compliant

Working temperature: ASTM C 1427-07 compliant from -94 F to +250 F

Wall thickness: 1/2" and 3/4"

Surface burning characteristics: **UL723 CLASSIFIED R39562** (ASTM E84 25/50), surface burning characteristics: flame spread 0, smoke developed 10. UL 94, top rated.

R-Value: between 6.0 and 4.0

UV: This product is **UL PERFORMANCE VERIFIED** for UV exposure (visit:<https://verify.ul.com>) and successfully tested internally for UV resistance against any major degradation, discoloration or deterioration for a minimum of 5 years.



SPECIAL FEATURES

Outer Jacket: Additional white polyethylene jacket cover protects foam insulation from tearing during installation process.

Foot Marking: Insulation incrementally marked by every foot to ensure accurate initial unit charge and reduce copper waste.

R410: Can be used in applications where high-pressure gases are used as a refrigeration source.

Paintable: The insulation can be painted to match the surroundings.



100% MADE IN THE USA

GelSpools™

TRY IT, LOVE IT.

PRODUCT TABLE

PDM US PART NUMBER	SIZE	INSULATION	SPOOL LENGTH (FT)	SPOOLS (per pallet)
GP-GUS-SP1412	1/4	1/2	3444	2
GP-GUS-SP3812	3/8	1/2	2624	2
GP-GUS-SP1212	1/2	1/2	2296	2
GP-GUS-SP5812	5/8	1/2	1804	2
GP-GUS-SP3412	3/4	1/2	1443	2
GP-GUS-SP7812	7/8	1/2	1443	2
GP-GUS-SP1434	1/4	3/4	1968	2
GP-GUS-SP3834	3/8	3/4	1640	2
GP-GUS-SP1234	1/2	3/4	1214	2
GP-GUS-SP5834	5/8	3/4	984	2
GP-GUS-SP3434	3/4	3/4	853	2
GP-GUS-SP7834	7/8	3/4	754	2